11321-P060US PATENT

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

- 1. (Original) A method comprising a step of irradiating carbon nanotubes with microwaves to yield a plurality of crosslinked carbon nanotubes.
- 2. (Original) The method of claim 1, wherein the step of irradiating is carried out in an inert environment selected from the group consisting of ultra-high vacuum, high vacuum, inert gases, and combinations thereof.
- 3. (Original) The method of claim 1, wherein the microwave radiation comprises a frequency that ranges from about 0.01 GHz to about 100 GHz.
- 4. (Currently amended) The method of elaims claim 3, wherein the frequency ranges from about 1 GHz to about 18 GHz.
- 5. (Original) The method of claim 1, wherein the microwave radiation is generated by a magnetron with a power that ranges from about 1 W to about 10,000 W.
- 6. (Original) The method of claim 5, wherein the power ranges from about 10 W to about 1,000 W.
- 7. (Currently amended) The method of claim 1, wherein the <u>plurality of crosslinked carbon</u> nanotubes <u>material</u> comprises at least one junction formed via the <u>a</u> rearrangement of carbon atoms.

11321-P060US PATENT

8. (New) A method comprising a step of irradiating carbon nanotubes with microwaves to yield a plurality of crosslinked carbon nanotubes, wherein crosslinking is generated between the sidewalls of adjacent carbon nanotubes.

- 9. (New) The method of claim 8, wherein the carbon nanotubes are single-wall carbon nanotubes.
- 10. (New) The method of claim 8, wherein the carbon nanotubes are chemically functionalized prior to the step of irradiating.
- 11. (New) The method of claim 8, wherein the crosslinking comprises covalent bonds.
- 12. (New) The method of claim 11, wherein the covalent bonds are carbon-carbon bonds.
- 13. (New) The method of claim 8, wherein the step of irradiating is carried out in an inert environment selected from the group consisting of ultra-high vacuum, high vacuum, inert gases, and combinations thereof.
- 14. (New) The method of claim 8, wherein the microwave radiation comprises a frequency that ranges from about 0.01 GHz to about 100 GHz.
- 15. (New) The method of claim 14, wherein the frequency ranges from about 1 GHz to about 18 GHz.
- 16. (New) The method of claim 8, wherein the microwave radiation is generated by a magnetron with a power that ranges from about 1 W to about 10,000 W.

11321-P060US PATENT

17. (New) The method of claim 16, wherein the power ranges from about 10 W to about 1,000 W.

18. (New) The method of claim 8, wherein the plurality of crosslinked carbon nanotubes comprises at least one junction formed via a rearrangement of carbon atoms.